

---

**Martensitic** (Hardenable by heat treatment)

410	General-purpose heat treatable type. Machine parts; pump shafts; bolts; brushings; coal chutes; cutlery; finishing tackle; hardware; jet engine parts; mining machinery; rifle barrels; screws; valves.	11.5-13.5 Cr, 0.15 C, 1.0 Mn, 1.0 Si, 0.040 P, 0.030 S	sheets	70,000	45,000	25	80 Rb	C	90
(S41000)			plates	70,000	35,000	30	150 Bhn		81

---

**Ferritic** (Non-hardenable)

430	General-purpose non-hardenable chromium type. Decorative trim; nitric acid tanks; annealing baskets; combustion chambers; dishwashers; heaters; mufflers; range hoods; recuperators; restaurant equipment.	16-18 Cr, 0.12 C, 1.0 Mn, 1.0 Si, 0.040 P, 0.030 S	sheets	75,000	50,000	25	85 Rb	C	87
(S43000)			plates	75,000	40,000	30	160 Bhn		84

---